API 572 RP – INSPECTION OF PRESSURE VESSELS PRACTICE TEST (SAMPLE)

STUDY GUIDE



SAMPLE STUDY GUIDE WITH LIMITED QUESTIONS

VISIT US ONLINE FOR THE FULL VERSION STUDY GUIDE

https://api572rp.examzify.com

Copyright © 2026 by Examzify - A Kaluba Technologies Inc. product.

ALL RIGHTS RESERVED.

No part of this book may be reproduced or transferred in any form or by any means, graphic, electronic, or mechanical, including photocopying, recording, web distribution, taping, or by any information storage retrieval system, without the written permission of the author.

Notice: Examzify makes every reasonable effort to obtain accurate, complete, and timely information about this product from reliable sources.

SAMPLE

Table of Contents

Copyright 1
Table of Contents 2
Introduction 3
How to Use This Guide 4
Questions 5
Answers 8
Explanations 10
Next Steps 16

SAMPLE

Introduction

Preparing for a certification exam can feel overwhelming, but with the right tools, it becomes an opportunity to build confidence, sharpen your skills, and move one step closer to your goals. At Examzify, we believe that effective exam preparation isn't just about memorization, it's about understanding the material, identifying knowledge gaps, and building the test-taking strategies that lead to success.

This guide was designed to help you do exactly that.

Whether you're preparing for a licensing exam, professional certification, or entry-level qualification, this book offers structured practice to reinforce key concepts. You'll find a wide range of multiple-choice questions, each followed by clear explanations to help you understand not just the right answer, but why it's correct.

The content in this guide is based on real-world exam objectives and aligned with the types of questions and topics commonly found on official tests. It's ideal for learners who want to:

- Practice answering questions under realistic conditions,
- Improve accuracy and speed,
- Review explanations to strengthen weak areas, and
- Approach the exam with greater confidence.

We recommend using this book not as a stand-alone study tool, but alongside other resources like flashcards, textbooks, or hands-on training. For best results, we recommend working through each question, reflecting on the explanation provided, and revisiting the topics that challenge you most.

Remember: successful test preparation isn't about getting every question right the first time, it's about learning from your mistakes and improving over time. Stay focused, trust the process, and know that every page you turn brings you closer to success.

Let's begin.

SAMPLE

How to Use This Guide

This guide is designed to help you study more effectively and approach your exam with confidence. Whether you're reviewing for the first time or doing a final refresh, here's how to get the most out of your Examzify study guide:

1. Start with a Diagnostic Review

Skim through the questions to get a sense of what you know and what you need to focus on. Your goal is to identify knowledge gaps early.

2. Study in Short, Focused Sessions

Break your study time into manageable blocks (e.g. 30 – 45 minutes). Review a handful of questions, reflect on the explanations.

3. Learn from the Explanations

After answering a question, always read the explanation, even if you got it right. It reinforces key points, corrects misunderstandings, and teaches subtle distinctions between similar answers.

4. Track Your Progress

Use bookmarks or notes (if reading digitally) to mark difficult questions. Revisit these regularly and track improvements over time.

5. Simulate the Real Exam

Once you're comfortable, try taking a full set of questions without pausing. Set a timer and simulate test-day conditions to build confidence and time management skills.

6. Repeat and Review

Don't just study once, repetition builds retention. Re-attempt questions after a few days and revisit explanations to reinforce learning. Pair this guide with other Examzify tools like flashcards, and digital practice tests to strengthen your preparation across formats.

There's no single right way to study, but consistent, thoughtful effort always wins. Use this guide flexibly, adapt the tips above to fit your pace and learning style. You've got this!

SAMPLE

Questions

SAMPLE

1. **Which type of insulated vessel has the highest likelihood of experiencing CUI?**

   A. CS vessel operating at 450°F

   B. CS vessel operating at 600°F but in intermittent service

   C. Low alloy steel vessel operating at 350°F

   D. Austenitic stainless steel vessel at 300°F

2. **Which type of pressure vessel inspection focuses on identifying wear over time?**

   A. Visual inspection

   B. Periodic integrity assessment

   C. Destructive testing

   D. Operational qualification testing

3. **Which inspection method should be avoided on vessels containing 5% H2S?**

   A. Visual inspection

   B. Ultrasonic testing

   C. Hammer testing

   D. Magnetic particle testing

4. **What factor is critical in assessing vessels for caustic embrittlement?**

   A. Type of inspection performed

   B. Temperature and stress level

   C. Size of the vessel

   D. Type of caustic material stored

5. **What is typically the most common cause of out of roundness in existing exchanger shells?**

   A. Corrosion over time

   B. Welding repairs to the shell

   C. Material fatigue

   D. Improper installation

SAMPLE

6. Erosion on a surface is characterized by which appearance?

A. Rough texture with dull finish

B. Uneven surface with pitting

C. Smooth surface with bright appearance

D. Cracked and brittle surface

7. How often should diameter measurements of a vessel skirt be taken to check for distortion?

A. 30°

B. 45°

C. 60°

D. 90°

8. Which of the following does not contribute to cracking in concrete foundations?

A. Moisture infiltration

B. Concrete corrosion

C. Thermal expansion

D. Soil settlement

9. Which testing method is effective for checking disbonded fireproofing?

A. Visual inspection

B. Hammer testing with light taps

C. Thermal imaging

D. Ultrasonic testing

10. What does the presence of residual water after a hydrotest indicate about potential issues?

A. It's safe to operate without concern

B. It may lead to microbiological corrosion

C. It is normal and requires no action

D. It signifies a failure in testing

SAMPLE

Answers

SAMPLE

1. B
2. B
3. C
4. B
5. B
6. C
7. C
8. B
9. B
10. B

SAMPLE

Explanations

SAMPLE

1. Which type of insulated vessel has the highest likelihood of experiencing CUI?

A. CS vessel operating at 450°F

B. CS vessel operating at 600°F but in intermittent service

C. Low alloy steel vessel operating at 350°F

D. Austenitic stainless steel vessel at 300°F

The type of insulated vessel that has the highest likelihood of experiencing Corrosion Under Insulation (CUI) is typically the one that operates under conditions most conducive to moisture accumulation and retention. In this scenario, a carbon steel (CS) vessel operating at 600°F but in intermittent service presents a significant risk for CUI. At elevated temperatures, such as 600°F, carbon steel is susceptible to CUI because moisture can infiltrate the insulation. When operating intermittently, the vessel can experience significant thermal cycling, which can lead to condensation forming within the insulation during cool-down periods. This condensation can lead to moisture retention, creating an ideal environment for corrosion to occur under the insulation, especially since carbon steel is highly prone to rust when exposed to water. In contrast, while options involving a CS vessel at 450°F and a low alloy steel vessel at 350°F are also vulnerable to CUI, the higher temperature and the intermittent operating nature of the 600°F scenario escalate the risk considerably. The austenitic stainless steel vessel at 300°F generally has a much lower likelihood of CUI due to its improved corrosion resistance compared to carbon steel varieties. Thus, the specific conditions of Option B contribute to its classification as having the highest likelihood of

2. Which type of pressure vessel inspection focuses on identifying wear over time?

A. Visual inspection

B. Periodic integrity assessment

C. Destructive testing

D. Operational qualification testing

Periodic integrity assessment is the correct focus for identifying wear over time in pressure vessels. This inspection method involves regular evaluations of the vessel's condition to monitor and assess any degradation or changes that have occurred since the last assessment. These assessments are designed to ensure the structural integrity and safety of the vessel over its operational life. The periodic nature of this type of assessment allows for the identification of trends in wear and potential failure mechanisms that can develop over time. By conducting these inspections at scheduled intervals, operators can take proactive steps to address issues before they lead to significant problems, thereby enhancing safety and extending the life of the equipment. Other options, while relevant in various contexts, do not specifically target the long-term observation of wear. For example, visual inspection can identify surface defects but may not adequately reveal the extent of wear or internal degradation over time. Destructive testing involves taking samples to evaluate material properties but is not suitable for regular monitoring since it can damage the vessel. Operational qualification testing focuses on validating that a vessel operates correctly under prescribed conditions, rather than monitoring wear over time.

SAMPLE

3. Which inspection method should be avoided on vessels containing 5% H2S?

A. Visual inspection

B. Ultrasonic testing

C. Hammer testing

D. Magnetic particle testing

The most appropriate choice for inspection methods that should be avoided on vessels containing 5% H2S is the hammer testing method. Hammer testing, often referred to in a broader sense as impact testing or the "ping" test, involves striking the surface of the vessel and listening to the sound produced to assess the material condition. In environments where hydrogen sulfide (H2S) is present, there is a significant risk of embrittlement and stress corrosion cracking. As a result, the integrity of the vessel's material can be compromised. When performing hammer testing in such conditions, you may inadvertently overlook serious flaws or damage because the method relies heavily on the operator's experience and subjective judgment regarding sound rather than concrete, quantifiable data. Moreover, the physical impact of hammer testing may exacerbate existing flaws, especially in materials weakened by H2S. Other inspection methods, such as visual inspection, ultrasonic testing, and magnetic particle testing, are generally more reliable and suitable for assessing the condition of pressure vessels in H2S environments, as they can provide more detailed and quantitative data regarding wall thickness and the presence of surface or subsurface flaws without adding stress to the material.

4. What factor is critical in assessing vessels for caustic embrittlement?

A. Type of inspection performed

B. Temperature and stress level

C. Size of the vessel

D. Type of caustic material stored

The factor that is critical in assessing vessels for caustic embrittlement is the temperature and stress level. Caustic embrittlement is a form of cracking that occurs in carbon steel when it is exposed to caustic soda solutions at elevated temperatures, particularly in the presence of residual stresses. Higher temperatures can exacerbate the embrittlement process, while the stress level in the material—stemming from factors such as operational loading, previous fabrication processes, or corrosion-related degradation—can make the material more susceptible to cracking. Understanding the interplay between temperature and stress is essential for predicting the likelihood of caustic embrittlement, enabling inspectors and engineers to make informed decisions about the integrity and safety of pressure vessels. This consideration allows for proper maintenance strategies and inspections aimed at identifying potential weaknesses that could lead to failure, ensuring the continued safe operation of vessels that handle caustic materials.

SAMPLE

5. What is typically the most common cause of out of roundness in existing exchanger shells?

A. Corrosion over time

B. Welding repairs to the shell

C. Material fatigue

D. Improper installation

The most common cause of out of roundness in existing exchanger shells is often linked to welding repairs to the shell. When repairs are made, especially if they involve significant welding, heat can be introduced to the material, leading to thermal expansion and contraction. This can alter the shape of the shell as the metal behaves differently after being heated and cooled, potentially leading to distortion or out of roundness. Additionally, welding processes can introduce residual stresses into the material, contributing to changes in its shape. Over time, these stresses may lead to permanent deformation, so the cumulative effects of welding on an exchanger shell can significantly impact its overall geometry. Understanding the relationship between welding and the physical integrity of pressure vessels is crucial in maintenance and inspection practices to ensure these components retain their intended performance characteristics.

6. Erosion on a surface is characterized by which appearance?

A. Rough texture with dull finish

B. Uneven surface with pitting

C. Smooth surface with bright appearance

D. Cracked and brittle surface

Erosion on a surface is characterized by a smooth surface with a bright appearance. This is a result of the continuous removal of material through the action of fluid flow or other mechanical processes, which can lead to a polished look as the softer materials are worn away. The term "bright appearance" in this context refers to the reflective quality of the surface that can develop when layers of material are gradually smoothed over time. In cases of erosion, specific forms of wear tend to polish the surface rather than create roughness or irregularities, which distinguishes it from other forms of damage, such as corrosion or impact wear. This polished state occurs as the material is gradually rounded off, exhibiting a smoother, shinier finish due to the consistent action of erosive forces acting on it. The other appearances mentioned, such as rough textures or brittleness, typically result from different forms of damage or degradation, like corrosion or other mechanical failures, rather than erosion.

SAMPLE

7. How often should diameter measurements of a vessel skirt be taken to check for distortion?

A. 30°

B. 45°

C. 60°

D. 90°

Taking diameter measurements of a vessel skirt at periodic intervals is essential for identifying any distortion or out-of-round conditions that may jeopardize the integrity of the pressure vessel. Measuring every 60 degrees allows for a thorough assessment of the skirt's condition while maintaining a balance between resource efficiency and comprehensive coverage of the structure. This choice is based on standard practices that recommend measuring at regular angular increments to ensure that the entire circumference is assessed without excessive expenditure of time or resources. A 60-degree interval offers a reasonable number of measurement points—six around the vessel—that can effectively highlight changes without over-complication. In contrast, measuring at smaller intervals, such as 30 degrees, could potentially lead to unnecessary work and may not provide significantly more useful data. On the other hand, larger intervals like 90 degrees would likely miss critical areas of distortion, making the assessment less reliable and could increase the risk of undetected issues. Therefore, measuring at 60 degrees strikes a balance that aligns with best practices in pressure vessel inspections.

8. Which of the following does not contribute to cracking in concrete foundations?

A. Moisture infiltration

B. Concrete corrosion

C. Thermal expansion

D. Soil settlement

Concrete corrosion is not typically a direct contributor to cracking in concrete foundations. Instead, it primarily refers to the deterioration of the concrete material itself due to various environmental factors, such as exposure to chlorides or sulfates, leading to a loss of strength and integrity over time. While corrosion can weaken a structure, it does not inherently cause cracking as moisture infiltration, thermal expansion, and soil settlement do. Moisture infiltration can lead to the freeze-thaw cycle, resulting in cracks as water expands when frozen. Thermal expansion causes concrete to expand and contract with temperature changes, which, if not properly accounted for through joint placement, can also lead to cracking. Soil settlement occurs when the supporting soil under the foundation compresses or shifts over time, leading to differential movement that can crack the concrete. Therefore, while all of the other factors are directly related to cracks appearing in concrete foundations, corrosion is more about the overall degradation of the concrete rather than a mechanism that directly induces cracking.

SAMPLE

9. Which testing method is effective for checking disbonded fireproofing?

A. Visual inspection

B. Hammer testing with light taps

C. Thermal imaging

D. Ultrasonic testing

The effectiveness of hammer testing with light taps for checking disbonded fireproofing lies in its ability to identify areas where the fireproofing material has separated from the substrate. When the hammer is tapped against the fireproofing, the sound produced and the response felt through the hammer can indicate the integrity of the bond between the fireproofing and the surface it is meant to protect. Disbonded areas typically resonate differently, often producing a dull sound or feeling, which suggests that the insulation is not adequately adhered. This method is straightforward and cost-effective, making it suitable for field applications. Inspectors can gather immediate feedback on the condition of the fireproofing without needing complex equipment. It is particularly useful because it can be performed quickly and does not require extensive preparation or setup. Other testing methods have their advantages, but they may not be as direct in assessing disbondment as hammer testing. Visual inspection may be limited by what is immediately observable, thermal imaging can identify temperature differences but might not specifically indicate disbonding, and ultrasonic testing can provide detailed material properties yet may be more complex to apply in real-world scenarios. Hence, hammer testing is a preferred choice for its practical effectiveness in identifying disbonded fireproofing.

10. What does the presence of residual water after a hydrotest indicate about potential issues?

A. It's safe to operate without concern

B. It may lead to microbiological corrosion

C. It is normal and requires no action

D. It signifies a failure in testing

The presence of residual water after a hydrotest raises concerns primarily because it may lead to microbiological corrosion. After a hydrostatic test, the vessel is filled with water to test its integrity, but if water remains trapped inside, it creates an environment that can support the growth of bacteria, particularly if organic materials are present. These bacteria can produce corrosive byproducts, which can significantly deteriorate the material of the vessel over time, leading to structural weaknesses and potential failure. This phenomenon emphasizes the importance of thorough drying and cleaning after hydrotesting to mitigate the risk of such corrosive activities occurring. While hydrotesting itself is critical for ensuring the integrity of pressure vessels, having residual water signifies that additional steps are necessary to prevent long-term maintenance issues. This understanding is crucial for maintaining operational safety and extending the service life of the equipment.

SAMPLE

Next Steps

Congratulations on reaching the final section of this guide. You've taken a meaningful step toward passing your certification exam and advancing your career.

As you continue preparing, remember that consistent practice, review, and self-reflection are key to success. Make time to revisit difficult topics, simulate exam conditions, and track your progress along the way.

If you need help, have suggestions, or want to share feedback, we'd love to hear from you. Reach out to our team at hello@examzify.com.

Or visit your dedicated course page for more study tools and resources:

https://api572rp.examzify.com

We wish you the very best on your exam journey. You've got this!

SAMPLE